



Hudson Valley Acoustics Laboratory

TEST REPORT

R100812S1

Standard: ASTM C423-07: Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method

Building 704, Boardman Road Site
2455 South Road, M/S P226
Poughkeepsie, New York 12601

2010 August 19

Phone: (845) 435-4959
FAX: (845) 432-9880

Client: FabriTrak Systems, Inc., 2553 Route 130 South, Suite 2, Cranbury, NJ 08512

Sound Absorption of Acoustical Wall Panel HVAL Test Number T100812T1

General

The IBM Hudson Valley Acoustics Laboratory is accredited to ISO/IEC 17025:2005 by the National Institute of Standards and Technology under its National Voluntary Laboratory Accreditation Program (NVLAP) for performing measurements according to the standardized test method described below. The test described in this report was conducted on 2010 August 12 at the IBM Hudson Valley Acoustics Laboratory in the Laboratory's 230-m³ Reverberation Room.

Standardized Test Method Followed


The measurements were performed in full conformance with ASTM C423-07, "Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method" with the following minor exception. The standard specifies a method for computing the reverberation time based on a linear first-order regression; instead, the IBM HVAL uses a proprietary algorithm built into its Norsonics NE830 real time analyzer. The ASTM C423 procedure is based on the fact that the decay rate (or reverberation time) of sound in a room is proportional to the sound absorption in that room. From measurements of the decay rates first in the empty room, and then in the room with the test specimen added, the absorption of the specimen can be calculated. A large number of repeated decay measurements is taken to ensure that the precision requirements of the standard are met.

Description of Test Specimens

The test specimens were provided directly by the client and consisted of:

1. Two identical panels of 1" thick, 6pcf fiberglass with a standard acoustically transparent fabric attached via the FabriTrak® system and adhered to a 5/8" thick sheet of gypsum board (sheetrock). Each panel measured 48" × 108" × 1 5/8"


A single test was conducted with the two panels lying flat on the reverberation room floor in the standardized Type A mounting. The two panels were butted together, with no spacing between panels, resulting in an overall sample area of 6.689 m² (72 ft²). The panels were tested with the fabric facing up into the sound field.

	Hudson Valley Acoustics Laboratory TEST REPORT	R100812S1
Standard: ASTM C423-07: Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method		
Building 704, Boardman Road Site 2455 South Road, M/S P226 Poughkeepsie, New York 12601	2010 August 19	Phone: (845) 435-4959 FAX: (845) 432-9880

Acoustical Data

The results are given in terms of sound absorption coefficients along with the computed values of the Sound Absorption Average, SAA, and the Noise Reduction Coefficient, NRC, as required by C423. For all the specimens tested here, the results are tabulated in Table 1 for the required 18 one-third octave-band test frequencies from 100 Hz through 5000 Hz.

A detailed record of the test conditions and results, and a complete description of the laboratory and measurement procedures are on file at the IBM Hudson Valley Acoustics Laboratory.

Submitted and Approved by 
Matthew A. Nobile
Technical Director
IBM Hudson Valley Acoustics Laboratory



Accredited to ISO/IEC 17025:2005 by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100323-0.

The results reported here relate only to the specific items tested. This report shall not be reproduced, except in full, without the written approval of the IBM Hudson Valley Acoustics Laboratory. The issuance of this report shall not be used by the client to claim product endorsement by NVLAP, NIST or any agency of the U.S. Government.



Hudson Valley Acoustics Laboratory

TEST REPORT

R100812S1

Standard: ASTM C423-07: Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method

Building 704, Boardman Road Site
2455 South Road, M/S P226
Poughkeepsie, New York 12601

2010 August 19

Phone: (845) 435-4959
FAX: (845) 432-9880

Table 1. Measured one-third octave band sound absorption coefficients per ASTM C423 and computed values of NRC and SAA.

Sound Absorption Coefficients per ASTM C423 using Type A Mounting	
Frequency (Hz)	Condition B: 1" fiberglass w/ SAT Fabric
100	0.12
125	0.19
160	0.16
200	0.29
250	0.39
315	0.54
400	0.83
500	0.94
630	0.97
800	1.02
1,000	1.02
1,250	1.02
1,600	0.98
2,000	0.95
2,500	0.92
3,150	0.91
4,000	0.89
5,000	0.89
NRC	0.85
SAA	0.82



Hudson Valley Acoustics Laboratory

TEST REPORT

R100812S1

Standard: ASTM C423-07: Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method

Building 704, Boardman Road Site
2455 South Road, M/S P226
Poughkeepsie, New York 12601

2010 August 19

Phone: (845) 435-4959
FAX: (845) 432-9880

Figure 1. Measured sound absorption coefficients per ASTM C423 for the conditions tested, as a function of frequency.

